

DM2514

Acid Catalysed Clear Parquet Timber Flooring Lacquer

DESCRIPTION & USES 2 pack acid catalysing, parquet flooring lacquer producing a tough finish with a high level of resistance to common household liquids. DM2514 is low odour and hydrocarbon free.

Recommended Application:

Internal hardwood or softwood floors in domestic or light commercial use. Not suitable for use on sports floors or areas where regular contact with water is likely, e.g. bathrooms.

DRY FILM PROPERTIES

Colour:

Clear

Gloss:

42% Semi-gloss (please contact us with other gloss level requirements)

WET PROPERTIES

Solid content:

52% (approx)

Viscosity in drum:

26-30 seconds Ford Cup 4 @ 20°C

Shelf life:

12 months in sealed containers

PREPARATION

New floors:

The surface to be finished must be clean, dry and free from contamination. Pre-sand using 100 or 120 grit paper and remove sanding dust.

Previously finished:

Not suitable for use on floors previously finished with Polyurethane Lacquer as severe yellowing may occur.

Procedure:

All traces of wax or polish must be removed. Ensure the previous coating is sound. Wash with white spirit to remove all traces of wax/polish and sand thoroughly using 100 or 120 grit paper. Ensure the surface is clean and dry and remove all sanding dust. It is recommended that a test area is finished to check adhesion of the lacquer to the previous coating. Ensure good ventilation if using white spirit to remove old polish. If in doubt, sand the floor back to bare timber, removing all the old coating then treat as a new floor.

APPLICATION

Method:

Stir well before use. Apply by brush or lambswool mop. Clean brushes or mops using an alcohol or ester rich thinner such as DT8900

Mixing ratio:

10 parts DM2514 to 1 part DV311 hardener

Thinning:

Do not thin (Ready to use)

Coverage & coats:

8-12 m2 per litre (approx)

Light Traffic: Apply 2 coats

Normal Traffic: Apply 3 coats

Heavy Traffic: Apply 4 coats

Drying:

Re-coatable: from 1 hour onwards at 20°C

Foot traffic: from 24 hours at 20°C

Full cure (required for rugs/furniture): 3 days (approx) at 20°C

Pot Life:

8 hours

MAINTENANCE

Vacuum clean or wipe with damp cloth or mop. Do not flood or over-wet the floor. If after a period of time, the floor starts to show signs of wear, a further coat of lacquer can be applied after preparation as detailed above.

FOR INDUSTRIAL USE ONLY Data shown are mean values and cannot be construed as product specifications. Users are advised to make their own tests to determine the suitability of products for their own purposes.

AUSTRALIAN DISTRIBUTORS FOR SHERWIN WILLIAMS

WA: TWENTY TWO SERVICES P/L

Tel (08) 9206 0220 **Fax** (08) 9206 0974

NSW: CROMA COATINGS

Tel (02) 9533 9122 **Fax** (02) 9533 9299

VIC: CROMA COATINGS VICTORIA

Tel (03) 9768 2312 **Fax** (03) 9768 2389

QLD: CROMA COATINGS QUEENSLAND

Tel (07) 3386 1000 **Fax** (07) 3386 1003

Email info@22croma.com.au

Web www.22croma.com.au