

NG808

Precatalysed Pigmented Topcoat

DESCRIPTION & USES One-component precatalysed pigmented topcoat (amino-alkyd and cellulose) with integral hardener. NG808 is formulated with low formaldehyde binders and low toxicity solvents to reduce risks with usage (contains NO aromatic hydrocarbons or Butanol).

Recommended Application:

For use as a topcoat over NF400 or DF1324.
Furniture, joinery, shop-fitting, wardrobe doors.
N.B Not recommended for use in wet areas (i.e kitchen benchtops , vanity tops etc)

DRY FILM PROPERTIES

Colour: White, can be tinted to most pastel colours

Gloss: Satin 30%

WET PROPERTIES

Solid content: 28% (approx)

Viscosity in drum: 28-35 seconds Ford Cup 4 @ 20°C

Shelf life: 12 months in sealed containers

APPLICATION

Method: Spraying conventional, curtain coating, roller coating

Thinning: DT8900 or BECKER22 at up to 20%
(Depending on type equipment used)
In hot/humid/rainy conditions NT573 can be added

Drying: Dust free: 5-10 minutes at 20°C
Sand to re-coat: 1-2 hours at 20°C or 20-30 minutes at 70°C
Stacking: 10-12 hours at 20°C or 1-2 hours at 70°C

NOTES

Ensure sufficient sanding of the primer is carried out if overcoating DF1324

FOR INDUSTRIAL USE ONLY Data shown are mean values and cannot be construed as product specifications. Users are advised to make their own tests to determine the suitability of products for their own purposes.

AUSTRALIAN DISTRIBUTORS FOR SHERWIN WILLIAMS

WA: TWENTY TWO SERVICES P/L **Tel** (08) 9206 0220 **Fax** (08) 9206 0974
NSW: CROMA COATINGS **Tel** (02) 9533 9122 **Fax** (02) 9533 9299
VIC: CROMA COATINGS VICTORIA **Tel** (03) 9768 2312 **Fax** (03) 9768 2389
QLD: CROMA COATINGS QUEENSLAND **Tel** (07) 3386 1000 **Fax** (07) 3386 1003

Email info@22croma.com.au
Web www.22croma.com.au