

Technical Data Sheet

Issue Date: June 16

TF4321

Polyurethane Pigmented Undercoat

DESCRIPTION & USES Polyurethane two-component white sealer for use on MDF and whiteboard. This

undercoat has high solids delivering very good surface build with excellent hiding power/coverage, good sandability and good vertical spraying characteristics. TF4321 is a fast curing, quick drying primer with good holdout, allowing efficient production schedules. Excellent coverage creates a good base on MDF for polyurethane topcoats.

Recommended

Application: For use under topcoats TH4401, TH4501. Furniture, joinery, shopfitting, wardrobe and

kitchen and vanity doors/benchtops, commercial interiors.

DRY FILM PROPERTIES

Colour: White

Gloss: N/A

WET PROPERTIES

Solid content: 69% (approx)

Viscosity in drum: 180 seconds Ford Cup 4 @ 20°C (approx)

Shelf life: 12 Months in sealed containers

APPLICATION

Method: Spraying conventional

Mixing Ratio: 2 Parts TF4321 to 1 Part TV4271 hardener

Thinning: THIN4230 or THIN4444 or THIN4000 at 15%-30% of part A

(Depending on type of equipment used)

Drying: Sand to re-coat: 4-5 hours at 20°C or 30-40 minutes at 50°C

Stacking: 5-6 hours at 20°C or 50-70 minutes at 50°C

Pot Life: 3-4 hours

Application weight: 120 - 180 g/m2

NOTES

FOR INDUSTRIAL USE ONLY Data shown are mean values and cannot be construed as product specifications. Users are advised to make their own tests to determine the suitability of products for their own purposes.

AUSTRALIAN DISTRIBUTORS FOR SHERWIN WILLIAMS

 WA:
 TWENTY TWO SERVICES P/L
 Tel (08) 9206 0220
 Fax (08) 9206 0974

 NSW:
 CROMA COATINGS
 Tel (02) 9533 9122
 Fax (02) 9533 9299

 VIC:
 CROMA COATINGS VICTORIA
 Tel (03) 9768 2312
 Fax (03) 9768 2389

 QLD:
 CROMA COATINGS QUEENSLAND
 Tel (07) 3386 1000
 Fax (07) 3386 1003

Email info@22croma.com.au Web www.22croma.com.au