

REPORT – RESULT OF ANALYSIS

Analysis performed by: Andrea Saltini
Analysis requested by: Andrea Manzini
Copy to: Sasha Seberry

Requested analysis: Analysis of volatile organic compounds (VOC) content (*)

Sample:

2K system white primer **EF4502-9001 + EV4345 hardener** (mixing ratio 100 : 5)

Result of Analysis:

Reference Method : **UNI EN ISO 11890-2 part 2** gas-chromatographic method ; **section 3.4** (product ready to use)

The sample was analysed using the **ISO 11890-2 part 2** and detected the following substances:

Substance	Weight %
Metoxy Propil Acetate (PMA)	0,9
Butylglycol	2,5
N-Ethyl Pyrrolidone	1,8
Propilen Glycol mono Butyl ether (PnB)	0,5

Total VOC amount = 5,7 %
Mix Density = 1,3 g/L
Total VOC = 74,1 g/L



Ernesto Balzarini, Laboratory Manager

(*) This is a laboratory analysis; please refer to MSDS for the theoretical VOC content