

**REPORT – RESULT OF ANALYSIS**

Analysis performed by: Andrea Saltini  
Analysis requested by: Andrea Manzini  
Copy to: Sasha Seberry

Requested analysis: Analysis of volatile organic compounds (VOC) content (\*)

---

**Sample:**

2K system white topcoat **EH4120-9001 + EV4345 hardener** (mixing ratio 100 : 10)

**Result of Analysis:**

Reference Method : **UNI EN ISO 11890-2 part 2** gas-chromatographic method ; **section 3.4** (product ready to use)

The sample was analysed using the **ISO 11890-2 part 2** and detected the following substances:

<b>Substance</b>	<b>Weight %</b>
Metoxy Propil Acetate (PMA)	1,7
Butylglycol	2
N-Ethyl Pyrrolidone	1,8
Butyl Di-Glycol	0,8

Total VOC amount = 6,3 %  
Mix Density = 1,175 g/L  
Total VOC = 74,1 g/L



Ernesto Balzarini, Laboratory Manager

(\*) This is a laboratory analysis; please refer to MSDS for the theoretical VOC content