

REPORT – RESULT OF ANALYSIS

Analysis performed by: Andrea Saltini
Analysis requested by: Andrea Manzini
Copy to: Sasha Seberry

Requested analysis: Analysis of volatile organic compounds (VOC) content (*)

Sample:

2K system clear sealer **EL4230 + EV4345 hardener** (mixing ratio 100 : 5)

Result of Analysis:

Reference Method : **UNI EN ISO 11890-2 part 2** gas-chromatographic method ; **section 3.4** (product ready to use)

The sample was analysed using the **ISO 11890-2 part 2** and detected the following substances:

Substance	Weight %
Metoxy Propil Acetate (PMA)	0,9
Butylglycol	2,1
N-Ethyl Pyrrolidone	1,8
Butyl Di-Glycol	0,8

Total VOC amount = 5,6%
Mix Density = 1,03 g/L
Total VOC = 57,7 g/L

Ernesto Balzarini, Laboratory Manager



(*) This is a laboratory analysis; please refer to MSDS for the theoretical VOC content