

SPRAYSTAIN

Dye Based - Spirit Stain

DESCRIPTION & USES Fast drying, non grain-raising, spirit based dye stains producing a clean vibrant and grain highlighting result. Colour density will vary depending on the colour, amount of applications and timber species.

Recommended Application:

For use as a stain under Becker Acroma precatylised, acid catalysed and polyurethane coatings. Refer to your technical representative for specific advice relating to timber species and application.

WET PROPERTIES

Standard Colours:

Baltic	470	Light Baltic	229
Teak	522	Maple	741
Golden Oak	502	Non-Fleck Jarrah	389
Jarrah	387	Walnut	439
Brown Walnut	482	Green Walnut	494
Rosewood	388	Red Mahogany	328

Most custom colours/shades can be made to order

Shelf life: 12 months in sealed containers

APPLICATION

Method: Designed to be sprayed at approximately 35psi

Thinning: Spraystains are supplied ready for use but can be reduced with DT8900/BECKER22

Use NT573 slow reducer for slower drying if required

Note: *If over-coating with polyurethane use THIN4444 or THIN4000 to dilute if required*

Clear Coating: Compatible to be over-coated with Becker Acroma precatylised, acid catalysing and polyurethane clear finishes

Toning: Dilute with DT8900/BECKER22 to weaken strength and spray mist coats where required

Drying: Before overcoating: 1-2 minutes at 20°C
Stacking: 10-20 minutes at 20°C

FOR INDUSTRIAL USE ONLY

Data shown are mean values and cannot be construed as product specifications.
Users are advised to make their own tests to determine the suitability of products for their own purposes.