

Issue Date: June 16

DH335

Care E1 Acid Catalysing Pigmented Semi-gloss Topcoat

DESCRIPTION & USES	Two-component acid catalyst semi-gloss pigmented topcoat (amino-alkyd and cel			
	for furniture and fittings. DH335 is formulated with low formaldehyde binders and low			
	toxicity solvents to reduce risks with usage (contains NO aromatic hydrocarbons or			
	Butanol). Suitable for surfaces that are to stand up to stringent demands, for example,			
	in accordance with the Furniture Fact System "Moblefakta." This high build topcoat has			
	excellent coverage and is fast drying ensuring efficient production results. Suitable for			
	automatic quick drying production lines. The stacking and packing of newly to surfaces can take place very quickly.			
Recommended				
Application:	For use over undercoat DF1324. Furniture, joinery, shop-fitting, wardrobe & kitchen doors, commercial interiors.			
	N.B Not recommended for use on wet areas (i.e kitchen benchtops , vanity tops etc)			

DRY FILM PROPERTIES

Colour:	White, can be tinted to most colours
Gloss:	Semi-gloss 50-60%

WET PROPERTIES

Solid content:	65% (approx)
Viscosity in drum:	150-160 seconds Ford Cup 4 @ 20°C
Shelf life:	12 months in sealed containers

APPLICATION

Method:	Spraying conventional, curtain coating	
Mixing Ratio:	7 parts DH335 to 1 part DV311 hardener	
Thinning:	DT8900 or BECKER22 at 25-35% (Depending on the type of equipment used) In hot/humid/rainy conditions NT573 can be added	
Pot Life:	1-2 days (approx)	
Drying:	16-20 hours at 20°C or 30-50 minutes at 70°C	

NOTES

Contact us for further information

FOR INDUSTRIAL USE ONLY Data shown are mean values and cannot be construed as product specifications. Users are advised to make their own tests to determine the suitability of products for their own purposes.

AUSTRALIAN DISTRIBUTORS FOR SHERWIN WILLIAMS

WA: TWENTY TWO SERVICES P/L	Tel (08) 9206 0220 Fax (08) 9206 0974	
NSW: CROMA COATINGS	Tel (02) 9533 9122 Fax (02) 9533 9299	Email info@22croma.com.au
VIC: CROMA COATINGS VICTORIA	Tel (03) 9768 2312 Fax (03) 9768 2389	Web www.22croma.com.au
QLD: CROMA COATINGS QUEENSLAND	Tel (07) 3386 1000 Fax (07) 3386 1003	