

Issue Date: July 16

## SM4006 METALLIC

Acrylic Polyurethane Clear Topcoat

DESCRIPTION & USES	<b>USES</b> Designer <b>metallic</b> finish made using our two component acrylic polyurethane clear topcoat for its excellent NON-YELLOWING properties. SM4006 provides good surface hardness, good moisture resistancy, very good smoothness to the touch and good covering power.			
Recommended Application:	For use over sealer SL4340 & SL4360. Furniture, joinery, shop-fitting, wardrobe and kitchen and vanity doors/benchtops, commercial interiors.			
DRY FILM PROPERTIES				
Colour:	Refer to our Metallic Colour Card. Other colours may be able to be matched-pls enquire.			
Gloss:	10%, 25%, 30%, 60%			
	As this metallic is made using a topcoat, it does not need to be clear coated afterwards. If you require a high gloss finish, overcoat SM4006-Metallic with <b>SC4220</b> up to 8 hours later. During this time period, SC4220 will bond/adhere to SM4006 Metallic without sanding and provide a tough, non-yellowing high gloss result. Please contact your technical representative for further information.			
WET PROPERTIES				
Solid content:	23% (approx)			
Viscosity in drum:	28-34 seconds Ford Cup 4 @ 20°C (approx)			
Shelf life:	12 Months in sealed containers			
APPLICATION				
Method:	Spraying conventional			
Mixing Ratio:	5 parts SM4006 to 1 part SV4310 hardener			
	or			
	10 parts SM4006 to 1 part SV4360 hardener (higher build – subject to availability)			
Thinning:	THIN4444 or THIN4000 at 10%-30% of part A (Depending on the type of equipment used) In hot conditions NT573 can be added			

**Drying:** Dry for stacking: 5-6 hours at 20°C or 80-90 minutes at 50°C

Pot Life:24 hours (approx)Application weight:100 - 140 g/m2

**FOR INDUSTRIAL USE ONLY** Data shown are mean values and cannot be construed as product specifications. Users are advised to make their own tests to determine the suitability of products for their own purposes.

## AUSTRALIAN DISTRIBUTORS FOR SHERWIN WILLIAMS

WA:	TWENTY TWO SERVICES P/L	Tel (08) 9206 0220	Fax (08) 9206 0974
NSW:	CROMA COATINGS	Tel (02) 9533 9122	Fax (02) 9533 9299
VIC:	CROMA COATINGS VICTORIA	Tel (03) 9768 2312	Fax (03) 9768 2389
QLD:	CROMA COATINGS QUEENSLAND	Tel (07) 3386 1000	Fax (07) 3386 1003

Email info@22croma.com.au Web www.22croma.com.au