

TM4060
Polyurethane Clear Topcoat

DESCRIPTION & USES Polyurethane two-component clear topcoat with excellent durability and resistance properties particularly against heat and moisture. Fast curing, excellent surface hardness and easy application on vertical surfaces. TM4060 uses 'low yellowing' hardeners designed specifically to reduce the yellowing of the coating itself. For protection against colour change of the timber substrate a UV prohibitor* can be added to TM4060 before application.

Recommended Application: For use over sealer TL4371 or TL4303. Furniture, joinery, shop-fitting, wardrobe and kitchen and vanity doors/benchtops, commercial interiors.

DRY FILM PROPERTIES

Colour: Clear
Gloss: 5%, 10%, 25%, 30%, 60%, 90%

WET PROPERTIES

Solid content: 35% (approx)
Viscosity in drum: 28-34 seconds Ford Cup 4 @ 20°C (approx)
Shelf life: 12 Months in sealed containers

APPLICATION

Method: Spraying conventional
Mixing Ratio: 2 Parts TM4060 to 1 Part TV4271 hardener (For TM4060-90% Gloss 2:1 TV4290 hardener)
Thinning: THIN4444 or THIN4000 at 30%-40% of part A (Depending on the type of equipment used) In hot conditions NT573 can be added
Drying: Stacking: 5-6 hours at 20°C or 70-90 minutes at 50°C
Pot Life: 12-15 hours
Application weight: 100 - 140 g/m²

NOTES

* UV Prohibitor should be added to the sealer TL4371 also
For further details and information please contact us.

FOR INDUSTRIAL USE ONLY Data shown are mean values and cannot be construed as product specifications. Users are advised to make their own tests to determine the suitability of products for their own purposes.

AUSTRALIAN DISTRIBUTORS FOR SHERWIN WILLIAMS

WA: TWENTY TWO SERVICES P/L **Tel** (08) 9206 0220 **Fax** (08) 9206 0974
NSW: CROMA COATINGS **Tel** (02) 9533 9122 **Fax** (02) 9533 9299
VIC: CROMA COATINGS VICTORIA **Tel** (03) 9768 2312 **Fax** (03) 9768 2389
QLD: CROMA COATINGS QUEENSLAND **Tel** (07) 3386 1000 **Fax** (07) 3386 1003

Email info@22croma.com.au
Web www.22croma.com.au