

NM800

Care E1 Precatalysed Clear Lacquer

DESCRIPTION & USES One component clear precatalysed lacquer available in matt to gloss finishes (amino-alkyd and cellulose resins) with integral hardener. NM800 is formulated with low formaldehyde binders and low toxicity solvents to reduce risks with usage (contains NO aromatic hydrocarbons or Butanol). NM800 can be used to both seal and topcoat and offers good build and a silky surface finish. This lacquer especially features excellent flexibility properties and is suitable for the wetting treatment of most types of wood.

Recommended Application:

For use as a lacquer for furniture, joinery, shop-fitting, wardrobe doors.
N.B Not recommended for use in wet areas (i.e kitchen benchtops , vanity tops etc)

DRY FILM PROPERTIES

Colour: Clear
Gloss: 10%, 30%, 60%

WET PROPERTIES

Solid content: 28% (approx)
Viscosity in drum: 28-35 seconds Ford Cup 4 @ 20°C
Shelf life: 12 months in sealed containers

APPLICATION

Method: Spraying conventional, curtain coating
Mixing Ratio: N/A
Thinning: DT8900 or BECKER22 at up to 20% (Depending on type equipment used)
In hot/humid/rainy conditions NT573 can be added
Pot Life: N/A
Drying: Sand to re-coat: 1-2 hours at 20°C or 25-30 minutes at 70°C
Stacking: 10-12 hours at 20°C or 1-2 hours at 70°C

NOTES We recommend using a polyurethane sealer when coating Beech and Tasmanian Blackwood
Ensure PU sealer is sufficiently sanded before topcoating with NM800
Contact us for further information

FOR INDUSTRIAL USE ONLY Data shown are mean values and cannot be construed as product specifications. Users are advised to make their own tests to determine the suitability of products for their own purposes.

AUSTRALIAN DISTRIBUTORS FOR SHERWIN WILLIAMS

WA: TWENTY TWO SERVICES P/L **Tel** (08) 9206 0220 **Fax** (08) 9206 0974
NSW: CROMA COATINGS **Tel** (02) 9533 9122 **Fax** (02) 9533 9299
VIC: CROMA COATINGS VICTORIA **Tel** (03) 9768 2312 **Fax** (03) 9768 2389
QLD: CROMA COATINGS QUEENSLAND **Tel** (07) 3386 1000 **Fax** (07) 3386 1003

Email info@22croma.com.au
Web www.22croma.com.au