

TH4501

Polyurethane Pigmented High Gloss Topcoat

DESCRIPTION & USES Polyurethane two-component pigmented high gloss topcoat with very good surface hardness, excellent water resistance, good resistance to marking, EXCELLENT hiding power and good smoothness to the touch. This gloss paint in white and light colours has excellent coverage from a high proportion of titanium dioxide pigment.

Recommended Application:

For use over PU undercoat TF4321 & TF4361 or Polyester P2299. Furniture, joinery, shop-fitting, wardrobe doors and kitchen and vanity doors/benchtops, commercial interiors.

DRY FILM PROPERTIES

Colour: White, can be tinted to most colours

Gloss: 90% Gloss

WET PROPERTIES

Solid content: 71% (approx)

Viscosity in drum: 115 seconds Ford Cup 4 @ 20°C (approx)

Shelf life: 12 Months in sealed containers

APPLICATION

Method: Spraying conventional

Mixing Ratio: 4 Parts TH4501 to 3 Parts TV4290 hardener

Thinning: THIN4444 at 30-40% of part A
(Depending on the type of equipment used)
In hot conditions NT573 can be added

Drying: 24 hours at 20°C or 5-6 hours at 50°C

Pot Life: 5-6 hours

Application weight: 140 - 180 g/m²

NOTES

FOR INDUSTRIAL USE ONLY Data shown are mean values and cannot be construed as product specifications. Users are advised to make their own tests to determine the suitability of products for their own purposes.

AUSTRALIAN DISTRIBUTORS FOR SHERWIN WILLIAMS

WA: TWENTY TWO SERVICES P/L **Tel** (08) 9206 0220 **Fax** (08) 9206 0974
NSW: CROMA COATINGS **Tel** (02) 9533 9122 **Fax** (02) 9533 9299
VIC: CROMA COATINGS VICTORIA **Tel** (03) 9768 2312 **Fax** (03) 9768 2389
QLD: CROMA COATINGS QUEENSLAND **Tel** (07) 3386 1000 **Fax** (07) 3386 1003

Email info@22croma.com.au
Web www.22croma.com.au