

| DESCRIPTION | |
|-----------------------------|--|
| Polyesthere white sealer. | |
| General features | Polyester white sealer with excellent filling properties, verticality, levelling, and sanding properties. Suitable for lacquering on MDF substrates, chipboards and porous woods. It can be applied on every kind of wood. Better for manual sanding with hot weather conditions. It is recommended the use of a filler before the application on woods and on low-quality and milled MDF substrates. |
| Appearance in can | White Liquid |
| Appearance of dry film | White Film |
| Storage | Containers must be stored tightly closed in a well-ventilated place with temperatures between 5°C and 35°C. |
| APPLICATION | |
| Application Method | By spraygun |
| Support preparation | Suitable to lacquer MDF substrates, porous substrates, and particle boards. Recommended the use of a filler before the application on woods and on low-quality and milled MDF substrates. |
| Application and dilution | Apply a coat of an insulator. The following day apply by spray gun 250 - 350 gr/mq of DPE099 accelerated at 2% thinned at 20% Acetone and then catalyzed at 2% After about 50 minutes, when the first coat is in GEL-TIME, apply a second coat as previously prepared. After about 12 hours sand with sandpaper 220 - 400 and apply a coat of topcoat. |
| Drying at 20°C | Drying Dust Free 50' Touch Free 2 h Sanding 12 h Overcoating 12 h Stackable 12 |
| PHYSICAL PROPERTIES AT 20°C | |
| Viscosity | 20 " +/- 3" DIN 8 |
| Specific Weight | 1,490 +/- 0,050 Kg/Lt |
| Solid Content | 94 +/- 3% |

Daas & Chemicals S.r.l.
daassrl.com

| HQ | Contact | Company fiscal data | Daas Group |
|---|---|---|--|
| Via delle Industrie 6 33074 Ceolini di Fontanafredda PN Italy | Phone +39 0434 565738 chemicals@daassrl.com chemicals@pec.daassrl.com | VAT# IT01719360933 REA PN99010 Cap. Sociale € 110.000,00 i.v. | Chile – France – Malaysia – Mexico – Philippines – Taiwan – USA |

| | |
|------------|--------------|
| Pot Life | Gel time 30' |
| Shelf Life | 8 Months |

*Information contained in this TDS are based on our best knowledge and cannot be construed as a guarantee commitment, since the means, tools, place of use and application conditions are beyond our control.
Given recommendations have to be considered general in nature. We therefore don't accept any liability for improper use of the product. In case of doubt carry out a preliminary test before proceeding to production on industrial scale.*

DAAS & CHEMICALS S.r.l. reserves the right to change or update this TDS without prior notice.

Users are kindly requested to check they have the current edition.

For any further info please contact our technical dept at: chemicals@daassrl.com

Date: Feb-2024

Product name

Doc name

Page 2 of 2

Daas & Chemicals S.r.l.
daassrl.com

| HQ | Contact | Company fiscal data | Daas Group |
|---|---|---|--|
| Via delle Industrie 6 33074 Ceolini di Fontanafredda PN Italy | Phone +39 0434 565738 chemicals@daassrl.com chemicals@pec.daassrl.com | VAT# IT01719360933 REA PN99010 Cap. Sociale € 110.000,00 i.v. | Chile – France – Malaysia – Mexico – Philippines – Taiwan – USA |