

DESCRIPTION	
Two-components polyurethane white matt thixotropic varnish, electrostatic	
General features	Two-components polyurethane white matt varnish with excellent covering properties, rapidity, softness, verticality, and non-yellowing properties. Particularly suitable to paint shaped parts where the sanding process has removed the angular parts. It is suitable for applications by electrostatic spray gun. Polyurethane white matt converter of our Tinto metric system. Suggested to paint bathroom furniture, kitchen doors, wardrobes, and doors for interior.
Appearance in can	White Liquid
Appearance of dry film	White Film
Storage	Containers must be stored tightly closed in a well-ventilated place with temperatures between 5°C and 35°C.
APPLICATION	
Application Method	By spraygun, airless, by electrostatic spraygun, by curtain coater
Application Ratio	Quantity 130 - 160 gr/mq Vertical Stability 120 gr/mq Catalysis HAR8211 at 50% by weight, 70% by volume Dilution 20% by weight,
Application and dilution	Apply two coats, 40' - 60' from one another, of polyurethane white sealer. After 8 - 12 h sand with sandpaper 220 - 400 and apply by spraygun 130 - 160 gr/mq of DPU063 - 30GLOSS, catalyzed at 50% by weight with HAR8211 thinned at 20%
Drying	Dust Free 15' Touch Free 60' Overcoating 12 h (if necessary) Stackable 6 - 8 h
PHYSICAL PROPERTIES AT 20°C	
Viscosity	35" +/- 3" DIN 6
Specific Weight	1,320 +/- 0,050 Kg/Lt
Solid Content	65% +/- 3%

Daas & Chemicals S.r.l.
daassrl.com

HQ	Contact	Company fiscal data	Daas Group
Via delle Industrie 6 33074 Ceolini di Fontanafredda PN Italy	Phone +39 0434 565738 chemicals@daassrl.com chemicals@pec.daassrl.com	VAT# IT01719360933 REA PN99010 Cap. Sociale € 110.000,00 i.v.	Chile – France – Malaysia – Mexico – Philippines – Taiwan – USA

Pot Life	>4Hours
Shelf Life	24 Months

*Information contained in this TDS are based on our best knowledge and cannot be construed as a guarantee commitment, since the means, tools, place of use and application conditions are beyond our control.
Given recommendations have to be considered general in nature. We therefore don't accept any liability for improper use of the product. In case of doubt carry out a preliminary test before proceeding to production on industrial scale.*

DAAS & CHEMICALS S.r.l. reserves the right to change or update this TDS without prior notice.

Users are kindly requested to check they have the current edition.

For any further info please contact our technical dept at: chemicals@daassrl.com

Date: Jan-2022

Product name

Doc name

Page 2 of 2

Daas & Chemicals S.r.l.
daassrl.com

HQ	Contact	Company fiscal data	Daas Group
Via delle Industrie 6 33074 Ceolini di Fontanafredda PN Italy	Phone +39 0434 565738 chemicals@daassrl.com chemicals@pec.daassrl.com	VAT# IT01719360933 REA PN99010 Cap. Sociale € 110.000,00 i.v.	Chile – France – Malaysia – Mexico – Philippines – Taiwan – USA