

## Technical Data Sheet

Issue Date: Feb17

## **TL4570**

## Clear Isolator Sealer

**DESCRIPTION & USES** Transparent polyurethane basecoat designed to have excellent wetting properties and

adhesion to resinous woods. This isolator has very good elasticity and its adhesion

properties make it suitable to use under PL4234 clear wax polyester.

Recommended

Application: For use under PL4234 wax polyester or PL4331 polyester basecoat

**WET PROPERTIES** 

Solid content: 16% (approx)

Viscosity in drum: 10 seconds FORD CUP 4 @ 20°C (approx)

Specific gravity: 0.88 kg/L (approx)

**Shelf life:** 12 months in sealed containers

**APPLICATION** 

Method: Spraying conventional

Mixing Ratio: 1 Part TL4570 to 1 Part TV4117 hardener

**Thinning:** No thinning required

**Drying:** Stacking: 12 hours at 20°C

For use under PL4234/PL4331: Leave TL4570 to dry 1-2 hrs before over coating with

PL4234/PL4331.

Note: Refer notes on TDS for PL4234/PL4331 in regards to drying times and if sanding of

TL4570 is required before over-coating.

Pot Life: 16-20 hours

**Application weight:** 60-100 g/m2

NOTES Refer TDS for PL4234 and PL4331

**FOR INDUSTRIAL USE ONLY** Data shown are mean values and cannot be construed as product specifications. Users are advised to make their own tests to determine the suitability of products for their own purposes.

## **AUSTRALIAN DISTRIBUTORS FOR SHERWIN WILLIAMS**

 WA:
 TWENTY TWO SERVICES P/L
 Tel (08) 9206 0220
 Fax (08) 9206 0974

 NSW:
 CROMA COATINGS
 Tel (02) 9533 9122
 Fax (02) 9533 9299

 VIC:
 CROMA COATINGS VICTORIA
 Tel (03) 9768 2312
 Fax (03) 9768 2389

 QLD:
 CROMA COATINGS QUEENSLAND
 Tel (07) 3386 1000
 Fax (07) 3386 1003

Email info@22croma.com.au
Web www.22croma.com.au